



4/20/2008

RELIABILITY MONITOR REPORT
FOR

MFN Dual Poly NPN Bipolar

MAXIM Integrated Products

120 San Gabriel Dr.
Sunnyvale, CA 94086

This Report was prepared by
Maxim Reliability Engineering

Summary:

The data in the tables that follow was generated as the result of an on-going Process Reliability Monitor. The specific products in this process monitor are:

MAX2102CWI+	MAX2208ECM+	MAX3790CCQ
-------------	-------------	------------

The calculated failure rate for devices using this process is:

FAILURE RATE: **MTTF (YRS): 38756** **FITS: 2.9**

The parameters used to calculate this failure rate are as follows:

Cf: 60% **Ea: 0.7** **Tu: 25 °C**

The reliability data follows and in this section is the detailed reliability data by stress. The reliability data section includes the latest data available. This report covers data between 4/1/2007 and 3/31/2008 .

Process Information:

Process Description: MFN Dual Poly NPN Bipolar

OPERATING LIFE

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
HIGH TEMP OP LIFE		MAX2102CWI+	135C, 5.25V	1000 HRS	44	0	
		MAX3790CCQ	135C, 5.25V	1000 HRS	77	0	
		MAX2208ECM+	135C, 5.25V	1000 HRS	79	0	
				Total:		0	

FAILURE RATE: **MTTF (YRS): 38756** **FITS: 2.9**