

4/17/2013



**RELIABILITY MONITOR REPORT
FOR**

MFN Poly Emitter Complementary Bipolar (CB30)

MAXIM INTEGRATED

**160 RIO ROBLES
SAN JOSE, CA 95134**

**This Report was prepared by
MAXIM INTEGRATED Reliability Engineering**

Summary:

The data in the tables that follow was generated as the result of an on-going Process Reliability Monitor. The specific products in this process monitor are:

MAX4434EUK+

The calculated failure rate for devices using this process is:

FAILURE RATE: MTTF (YRS): 15503 QUANTITY: 80 FAILS: 0 FITS: 7.4

The parameters used to calculate this failure rate are as follows:

Cf: 60% Ea: 0.7 Tu: 25 °C

The reliability data follows and in this section is the detailed reliability data by stress. The reliability data section includes the latest data available. This report covers data between 4/1/2012 and 3/31/2013 .

Process Information:

Process Description: MFN Poly Emitter Complementary Bipolar (CB30)

OPERATING LIFE

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	LOT NO.
HIGH TEMP OP LIFE	1005	MAX4434EUK+	135°C	1000 HRS	80	0	N2MADA006E#
Total:						0	
FAILURE RATE:	MTTF (YRS): 15503		QUANTITY: 80	FAILS: 0	FITS: 7.4		